



DATA SHEET
DS 100
Rev. 04 dd 10/03/09
INETIG S2

I.N.E. S.p.A.
Via Facca 10
35013 Cittadella (PADOVA)
ITALY
Tel. : +39 049/9481111 Fax: + 39 049/9400249
Internet: www.ine.it E mail: ine@ine.it

CLASSIFICATION

APPROVALS

AWS SPECIFICATIONS	EN SPECIFICATIONS
AWS A 5.18: ER70S-2	EN ISO 636-A: W 46 4 W2Ti

ALLOY TYPE

Copper-coated tig rod for welding carbon and carbon-manganese steels.

APPLICATIONS

Copper-coated tig rod designed for welding carbon and carbon-manganese steels with tensile strength up to 510 MPa. Suitable as well for welding thin, galvanised or electro-galvanised plates; very limited spattering thanks to the addition of titanium and zirconium. The fusion allows the degassing of zinc vapours, which prevents the formation of blows and pores in the weld bead. It is used in root pass and to support the welding when no back pass is possible. Excellent mechanical and toughness properties when in low temperature conditions.

MATERIALS TO BE WELDED

ASTM		EN		Others
A139	A131 Gr A, B, D	10113-2 S275	10113-3 S420M	Fe 360
A210 Gr A1	API 5LX42	10113-2 S355	10113-3 S420ML	Fe 430
A210 Gr C	API 5LX46	10113-2 S420	10025 S185, S235	Fe 510
A36	API 5LX52	10113-3 S275M	10025 S275, S355	(steel group 1
A234 Gr WPB	API 5LX60	10113-3 S275ML	10208-1 L210, L240	EN 288/3)
A334 Gr 1		10113-3 S355M	10208-1 L290, L360	
A106 Gr A, B, C		10113-3 S355ML		

WELDING GUIDELINES

Preheat and PWHT are not required.

TECHNICAL INFORMATION

Gas: Argon 100% (EN ISO 14175)
Welding position: all positions



WELDING PARAMETERS

Current	DC - Straight polarity
----------------	-------------------------------

PACKAGING DATA

Diameter (mm)	1.2	1.6	2.0	2.4	3.2	4.0
Length (mm)	1000	1000	1000	1000	1000	1000
Carton	5/25 Kg	5/25 Kg	5/25 Kg	5/25 Kg	5/25 Kg	5/25 Kg

* tolerances according to EN ISO 544 specification.



DATA SHEET
DS 100
Rev. 04 dd 10/03/09
INETIG S2

I.N.E. S.p.A.
Via Facca 10
35013 Cittadella (PADOVA)
ITALY
Tel. : +39 049/9481111 Fax: + 39 049/9400249
Internet: www.ine.it E mail: ine@ine.it

TYPICAL CHEMICAL COMPOSITION OF WIRE

C %	Mn %	Si %	S %	P %	Cu %	Ti %	Zr %	Al %	
0.06	1.20	0.50	0.012	0.012	0.15	0.10	0.09	0.10	

TYPICAL MECHANICAL PROPERTIES

GAS		Yield strength	Tensile strength	Elongation on % 5d	Impact energy (Charpy V)				
		Rs	Rm	A 5d	+ 20°C	0°C	-20°C	-30°C	-40°C
		(MPa)	(MPa)	%	(Joule)	(Joule)	(Joule)	(Joule)	(Joule)
Argon	as welded	490	600	28	200	-	120	100	70

PRODUCTS AVAILABLE

Process	Product	Classification AWS	Classification EN
MIG/MAG Solid wire	INEFIL S2	AWS A 5.18: ER70S-2	EN 14341-A: G2Ti
	INEFIL 13.7	AWS A 5.18: ER70S-3	EN 14341-A: G2Si
	INEFIL S4	AWS A 5.18: ER70S-4	EN 14341-A: G3Si1
	INEFIL	AWS A 5.18: ER70S-6	EN 14341-A: G3Si1
	INEFIL 19.12	AWS A 5.18: ER70S-6	EN 14341-A: G4Si1
	INE SPEEDFIL	AWS A 5.18: ER70S-6	EN 14341-A: G3Si1
	INEFIL NR	AWS A 5.18: ER70S-6	EN 14341-A: G3Si1
	INEFIL 19.12 NR	AWS A 5.18: ER70S-6	EN 14341-A: G4Si1
TIG Rods	INETIG 13.7	AWS A 5.18: ER70S-3	EN 636-A: W2Si
	INETIG	AWS A 5.18: ER70S-6	EN 636-A: W3Si1
SAW Submerged arc	INESUB S2	AWS A 5.17: EM12	EN 756: S 2
	INESUB S2Si	AWS A 5.17: EM12K	EN 756: S 2Si
	INESUB S3Si	AWS A 5.17: EH12K	EN 756 S 3Si
FCAW Cored wire	INETUB R71T1	AWS A 5.20: E71T1	EN 17632-A: T 46 2 P M 1 H5
	INETUB R70T1	AWS A 5.20: E70T1	EN 17632-A: T 42 2 R M 3 H5
	INETUB R71T1-CO2	AWS A 5.20: E71T1	EN 17632-A: T 46 2 P C 1 H5
	INETUB M71TG	AWS A 5.18: E70C-6MH4	EN 17632-A: T 42 2 M M 1 H5
	INETUB B71T5	AWS A 5.20: E71T5	EN 17632-A: T 46 4 B M H5
SMAW Electrodes	INE 50 B	AWS A 5.1: E7018	EN 2560-A: E 42 4 B 42 H5
	INE 55 B	AWS A 5.1: E7018-1	EN 2560-A: E 42 4 B 42 H5