



PRODUCTS

BRASS ALLOYS

CODE	COMPOSITION %							MELTING POINT	TENSILE STRNGTH	CORRESPONDING STANDARDS
	Cu	Zn	Ag	Ni	Mn	Sn	Si	°C	Kg/mm2	EN 1044
WELD 1	60	39,8					0,2	890-910	40	CU 301
WELD 2	60	39,35			0,25	0,2	0,2	870-890	45	CU 303
WELD 3	60	39,35		1	0,25	0,3	0,2	870-890	40	CU 304
WELD 104	57	37,7		5			0,3	860-890	45	
WELD 110	48	41,4		10	0,2	0,2	0,2	910-930	54	CU 305

CHARACTERISTIC MAKE UP

Bare rods	ø 0,7 - 9 mm	Length standard: 500 mm 1000 mm
Fluxcoated rods	ø 1,5 - 2 - 3,2 mm	Length standard: 500 mm
Wires	ø 0,5 - 5 mm Coils and Spools	
Rings	on demand	

SALDFLUX S.r.l | Via Friuli 5, 20090 Fizzonasco di P.E. , Milano – ITALY
 Sede Legale e Uffici Italia: tel. 02-907 81 812 | fax 02-907 84 933 P. iva: 08049640967
 webdesign::office